E/Z Prime 895Î MATERIAL SAFETY DATA SHEET

APPLICATION

Water-Soluble Extrusion Coating Primer and Lamination Adhesive for Aluminum Foil to Film Applications

Chemical Name: Water based, modified ethylene acrylic acid copolymer dispersion

PRODUCT DESCRIPTION 6

Milky white liquid solution

Emergency Telephone Number: 1-800-424-9300 - Chemtrec

Manufacturer Telephone Number: 1-800-797-9244

HAZARDOUS INGREDIENTS/IDENTITY INFORMATION

Component Identity OSHA PEL ACGIH TLV %

Proprietary Resin. No ingredients in levels that are harmful.

HEALTH INFORMATION & FIRST AID TREATMENT

FIRST AID: -

EYE CONTACT: Flush with water

SKIN CONTACT: Wash with water

INHALATION: Remove to fresh air

INGESTION: Call medical professional

HEALTH HAZARDS 6 TOXICOLOGY:-

Ammonia vapors may cause irritation to the skin, eyes and respiratory tract.

E/Z Prime 895Î

MATERIAL SAFETY DATA SHEET

PERSONAL PROTECTION

Use safety glasses Plastic or rubber gloves

Use a NIOSH approved cartridge respirator if TLV or PEL is exceeded ó Mechanical exhaust recommended

FIRE AND EXPLOSION HAZARD DATA

Flash Point: N/A

Explosive Limits: Non explosive

SPILL CONTROL PROCEDURE

Flush material with water to drain or sewer

PHYSICAL & CHEMICAL PROPERTIES

Chemical Name: None (Material is a proprietary mixture)

Density: 0.991

Specific Gravity (Water = 1): 0.99

Boiling Point: 212° F/ 100°C

Evaporation Rate: Same as water

Viscosity Of Liquid: 70-90 cps

Freezing/Melting Point: Freezes at 32° F/0°C

pH: 9.0-10.5

Solids: 19.80-20%

E/Z Prime 895Î

MATERIAL SAFETY DATA SHEET

REACTIVITY DATA

Stability: Stable

Incompatibility: Acids and oxidizing agents

Hazardous Decomposition or Byproducts: None known to occur

Conditions: Protect from Freezing

TRANSPORTATION & STORAGE

Usual Shipping Containers: 55 gallon drums or 300 gallon totes

Storage Temperature: 40°F/10°C to 85°F/38°C

Transport Temperature: must be above freezing ó fully recoverable if frozen

The information herein is given in good faith and to the best of our knowledge. No warranty, express or implied, is made.